

Low pressure grade RO element for brackish water




• Low-Energy Consumption



SPECIFICATIONS •

General Features	
Permeate Flow Rate	12,000 GPD (45.4 m ³ /day)
Nominal Salt Rejection	99.5% (Minimum 99.4%)
Effective Membrane Area	400ft ² (37.2 m ²)
Membrane Type	Thin-Film Composite
Membrane Material	Polyamide (PA)
Element Configuration	Spiral-Wound, FRP Wrapping

Test Conditions: 1,500 mg/L NaCl solution at 150 psig (1.03 MPa) applied pressure; 15% recovery; $77^{\circ}F(25^{\circ}C)$; pH 6.5–7.0; Permeate flow rate for each element may vary +25 / -15%.



Each membrane element supplied with one interconnector (coupler) and four O-rings
All RE8040 elements fit nominal 8.0 inch (203.2 mm) I.D. pressure vessels.

Toray Advanced Materials Korea Inc.

For more information on our products, company and regional contacts, please visit our website at <u>www.csmfilter.com</u>. Product Specification Sheet / Model RE8040-BLN

PT Watermart Perkasa Email: sales@water.co.id Phone: +62-21-316-1671 Whatsapp (text only): +62815-8609-3500 Website: www.water.co.id

RE8040-BLN



Low pressure grade RO element for brackish water

APPLICATION DATA -

Operating Limits

Max. Pressure Drop / Element	15 psi (0.10 MPa)
Max. Pressure Drop / 240" Vessel	60 psi (0.41 MPa)
Max. Operating Pressure	600 psi (4.14 MPa)
Max. Feed Flow Rate	75 gpm (17.0 m ³ /hr)
Min. Concentrate Flow Rate	16 gpm (3.6 m³/hr)
Max. Operating Temperature	113°F (45°C)
Operating pH Range	2.0 - 11.0
CIP pH Range	1.0 - 13.0
Max. Turbidity	1.0 NTU
Max. SDI (15 min)	5.0
Max. Chlorine Concentration	< 0.1 mg/L
	c.O

GENERAL HANDLING PROCEDURES

- Elements contained in the boxes must be kept dry at room temperature (7–32°C; 40–95°F) and should not be stored in direct sunlight.
- For WET-TYPE, the preservative solution (1% sodium metabisulfite solution) is added to prohibit the growth of micro-organisms.
- Permeate from the first hour of operation should be discarded.
- Salt rejection would be stabilized within 48 hours of continuous operation depending on feedwater and operating conditions, but may take over a week for dry elements.

- Keep elements moist at all times after initial wetting.
- Avoid excessive pressure and flow spikes.
- Only use chemicals compatible with the membrane elements and components. Use of such chemicals may void the element limited warranty.
- Permeate pressure must always be equal or less than the feed/concentrate pressure. Damage caused by permeate back pressure voids the element limited warranty.
- The element shell is FRP(Fiber Reinforced Plastic). Be aware of glass fiber strands and use safety equipment.



Toray Advanced Materials Korea Inc. For more information on our products, company and regional contacts, please visit our websi Product Specification Sheet / Model RE8040-BLN



PT Watermart Perkasa Email: sales@water.co.id Phone: +62-21-316-1671 Whatsapp (text only): +62815-8609-3500 Website: www.water.co.id