

## GREENSAND<sup>plus</sup>™

### Performance Media for Water Filtration

**Removes iron, manganese, hydrogen sulfide, arsenic and radium.**

GreensandPlus™ is a black filter media used for removing soluble iron, manganese, hydrogen sulfide, arsenic and radium from groundwater supplies.

The manganese dioxide coated surface of GreensandPlus acts as a catalyst in the oxidation reduction reaction of iron and manganese.

The silica sand core of GreensandPlus allows it to withstand waters that are low in silica, TDS and hardness without breakdown.

GreensandPlus is effective at higher operating temperatures and higher differential pressures than standard manganese greensand. Tolerance to higher differential pressure can provide for longer run times between backwashes and a greater margin of safety.

Systems may be designed using either vertical or horizontal pressure filters, as well as gravity filters.

GreensandPlus is a proven technology for iron, manganese, hydrogen sulfide, arsenic and radium removal. Unlike other media, there is no need for


extensive preconditioning of filter media or lengthy startup periods during which required water quality may not be met.

GreensandPlus is an exact replacement for manganese greensand. It can be used in CR or IR applications and requires no changes in backwash rate (


times or chemical feeds.

GreensandPlus has the WQA Gold Seal Certification for compliance with NSF/ANSI 61. Packaging is available in 1/2 cubic foot bags or 1 metric ton (2,205 lbs)

### GREENSANDPLUS PRESSURE DROP (CLEAN BED)



### BED EXPANSION DURING BACKWASHING



## PHYSICAL CHARACTERISTICS

### Physical Form

Black, nodular granules shipped in a dry form

### Apparent Density

88 pounds per cubic foot net

### Shipping Weight

90 pounds per cubic foot gross

### Specific Gravity

Approximately 2.4

### Porosity

Approximately 0.45

### Screen Grading (dry)

18 X 60 mesh

### Effective Size

0.30 to 0.35 mm

### Uniformity Coefficient

Less than 1.60

### pH Range

6.2-8.5 (see General Notes)

### Maximum Temperature

No limit

### Backwash Rate

Minimum 12 gpm/sq. ft. at 55°F

### Service Flow Rate


2 – 12 gpm/sq. ft.

### Minimum Bed Depth

15 inches of each media for dual media beds or 30 inches of GreensandPlus alone.

## METHOD OF OPERATION CO

GreensandPlus: Catalytic Oxidation (CO)



Catalytic Oxidation (CO) operation is recommended in applications where iron removal is the main objective in well waters with or without the presence of manganese. This method involves the feeding of a predetermined amount of chlorine ( $\text{Cl}_2$ ) or other strong oxidant directly to the raw water before the GreensandPlus Filter.

Chlorine should be fed at least 10-20 seconds upstream of the filter, or as far upstream of the filter as possible to insure adequate contact time. A chlorine residual carried through the filter will maintain GreensandPlus in a continuously regenerated condition.

**For operation using chlorine, the demand can be estimated as follows:**

$$\text{mg/L Cl}_2 = (1 \times \text{mg/L Fe}) + (3 \times \text{mg/L Mn}) + (6 \times \text{mg/L H}_2\text{S}) + (8 \times \text{mg/L NH}_3)$$



## SUGGESTED OPERATING CONDITIONS

### Bed Type

Dual media: anthracite 15-18 in. and GreensandPlus 15-24 in.

### Capacity

700-1200 grains of oxidized iron and manganese/sq.ft. of bed area based on oxidant demand and operation to iron break through or dp limitations.

### Backwash

Sufficient rate using treated water to produce 40% bed expansion for 10 minutes or until waste water is clear.

### Air/Water Scour

Optional using 0.8-2.0 cfm/sq. ft. with a simultaneous treated water backwash at 4.0-4.5 gpm/sq. ft.

### Raw Water Rinse

At normal service flow rate for 3 minutes or until effluent is acceptable.

### Flow Rate

Recommended flow rates with CO operation are 2-12 gpm/sq. ft. Extremely high concentrations of iron and manganese usually require lower flow rates for equivalent run lengths. Higher flow rates can be considered with very low concentrations of iron and manganese. For optimizing design parameters, pilot plant testing is recommended. The run length between backwashes can be estimated as follows:

What is the run length for a water containing 1.7 mg/L iron and 0.3 mg/L manganese at a 4 gpm/sq. ft. service rate:

#### Contaminant loading

$$\begin{aligned} &= (1 \times \text{mg/L Fe}) + (2 \times \text{mg/L Mn}) \\ &= (1 \times 1.7) + (2 \times 0.3) \\ &= (2.3 \text{ mg/L or } 2.3/17.1 = 0.13 \\ &\quad \text{grains/gal. (gpg)}) \end{aligned}$$

$$\begin{aligned} &\text{At } 1,200 \text{ grains / sq. ft. loading} \div 0.13 \text{ gpg} \\ &= 9,230 \text{ gal./sq. ft.} \end{aligned}$$

$$\begin{aligned} &\text{At } 4 \text{ gpm / sq. ft. service rate } 9,230/4 \\ &= 2,307 \text{ min.} \end{aligned}$$

The backwash frequency is approximately every 32-38 hours of actual operation.

*The Intermittent regeneration (IR) operation is available for certain applications. Contact your Inversand representative for additional information.*

## GENERAL NOTES

### pH

Raw waters having natural pH of 6.2 or above can be filtered through GreensandPlus without pH correction. Raw waters with a pH lower than 6.2 should be pH-corrected to 6.5-6.8 before filtration. Additional alkali should be added following the filters if a pH higher than 6.5-6.8 is desired in the treated water. This prevents the possible adverse reaction and formation of a colloidal precipitate that sometimes occurs with iron and alkali at a pH above 6.8.

### Initial Conditioning of GreensandPlus

GreensandPlus media must be backwashed prior to adding additional media types. The GreensandPlus backwash rate must be a minimum of 12 gpm/sq. ft. @ 55 °F.

This initial backwash could last for up to 60 minutes to thoroughly remove the fine dust. After backwashing is complete, the GreensandPlus must be conditioned. Mix 0.5 gal. (1.9 L) of 6% household bleach or



## Initial Conditioning of GreensandPlus

0.2 gal (0.75 L) of 12% sodium hypochlorite for every 1 cu. ft. (28.3 L cu. m) of GreensandPlus into 6.5 gallons (25 L) of water.

Drain the filter enough to add the diluted chlorine mix. Apply the diluted chlorine to the filter being sure to allow the solution to contact the GreensandPlus media. Let soak for a minimum of 4 hours, then rinse to waste until the "free" chlorine residual is less than 0.2 mg/L. The GreensandPlus is now ready for service.

## Radium and Arsenic Removal Using GreensandPlus

The GreensandPlus CO process has been found to be successful in removing radium and arsenic from well water. This occurs via adsorption onto the manganese and/or iron precipitates that are formed. For radium removal, soluble manganese must be present in or added to the raw water for removal to occur. Arsenic removal requires iron to be present in or added to the raw water to accomplish removal. Pilot plant testing is recommended in either case.

## REFERENCES

### USA

American Water Company, CA  
San Jacinto, CA  
City of Tallahassee, FL  
City of Mason City, IL  
City of Goshen, IN  
City of Hutchinson, KS  
City of Burlington, MA  
Dedham Water Co., MA  
Raynham Center, MA  
Northbrook Farms, MD  
Sykesville, MD  
City of New Bern, NC  
Onslow County, NC  
Fort Dix, NJ  
Jackson Twsp. MUA, NJ  
Churchill County, NV  
Suffolk County Water Authority, NY  
City of Urbana, OH

### International

Ozogram, Laval, Quebec, Canada  
Sydney, Nova Scotia, Canada  
PT Besflo Prima, Jakarta, Indonesia  
Eurotrol, Milanese, Italy  
Gargon Industrial, Mexico City, Mexico  
Water Tec of Mexico, Veracruz, Mexico  
Filtration Tech, Auckland, New Zealand  
Alamo Water Poland, Izabelin, Poland  
Impulse Group, St. Petersburg, Russia  
Brenntag Nordic, Taby, Sweden  
Nema Kimya, Istanbul, Turkey  
Minh Tam, Ho Chi Minh, Vietnam



*The manufacturing of GreensandPlus is an ongoing, 24/7 process to ensure the highest quality water treatment media.*

**Inversand Company**  
SINCE 1925

226 Atlantic Avenue • P.O. Box 650 • Clayton, NJ 08312 USA

Tel: **856-881-2345** • Fax: **856-881-6859** • Email: [info@inversand.com](mailto:info@inversand.com) • [www.inversand.com](http://www.inversand.com)

