PRODUCT DATA SHEET

Purolite[™] Purofine[™] PFA400MBOH

Polystyrenic Gel, Type I Strong Base Anion Resin, Hydroxide form, Uniform Particle Size, Mixed Bed Grade

PRINCIPAL APPLICATIONS

- Demineralization
- Mixed Bed anion component

ADVANTAGES

- High operating capacity
- Good resistance to organic fouling
- Uniform particle size
- Antistat treated for easier separation from cation component

TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Type I Quaternary Ammonium
Ionic Form	OH-
Total Capacity (min.)	1.3 eq/L (28.4 Kgr/ft³) (Cl⁻ form)
Moisture Retention	48 - 54 % (CF form)
Mean Diameter	625 ± 55 μm
Uniformity Coefficient	1.1 - 1.2
Reversible Swelling, $CI^- \rightarrow OH^-$ (max.)	30 %
Specific Gravity	1.07
Shipping Weight (approx.)	670 - 700 g/L (41.9 - 43.8 lb/ft³)
Temperature Limit	100 °C (212.0 °F) (Cl⁻ form)
Temperature Limit	60 °C (140.0 °F) (OH⁻ form)





PT Watermart Perkasa Email: sales@water.co.id Phone: +62-21-316-1671 Whatsapp (text only): +62815-8609-3500 Website: www.water.co.id



Ecolab is a global developer, manufacturer, and supplier of Purolite[™] Resins including ion exchange, catalyst adsorbent and advanced polymers that make the world cleaner and healthier.

Purolite Resins Headquarters Ecolab Headquarters King of Prussia, PA St. Paul, MN Llantrisant, Wales Pharma Resin Manufacturing Philadelphia, PA ndustrial Resin Manufacturing Huzhou, China Victoria, Romania Industrial + Pharma Resin ndustrial + Pharma Re Manufacturing King of Prussia, PA Manufacturing Pharma Resin Manufacturing Landenberg, PA MMM Water harma Resin Manufacturing

We're ready to solve your process challenges.

For further information on products and services, visit <u>www.puroliteresins.com</u> or complete a Contact Us form via <u>PuroliteResins.com/contact-us</u> or use the QR code.

Contact Us Form:



The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.



2025 Purolite All rights reserved.

www.puroliteresi



PT Watermart Perkasa Email: sales@water.co.id Phone: +62-21-316-1671 Whatsapp (text only): +62815-8609-3500 Website: www.water.co.id